

LINTEC Technical Information

1. Product : R series

2. Emboss No. : R-120 #

#: LINTEC (SUZHOU) TECH CORPORATION Products

3. Specification:

Grade	Basis Weight (g/㎡)	Thickness (μm)	Glossiness (%)
LXD	180 ± 10	270 ± 20	32 ± 3
PXDH	175 ± 10	270 ± 20	32 ± 3

This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty.

Grade	Release Type	Application	Recommended Temperature
EV130TPD	Polyolefin	PU	110 – 130°C
LXD			110 – 130°C
PXDH / PXDL		PU, Semi-PU, PVC	190 – 210°C
VX	Special Resin	PVC	190 – 210°C
ENPLUS		PU, Semi-PU, PVC	190 – 210°C

-Notes

The statements in this technical information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications, customers should independently determine the suitability of this material for their specific purpose, Prior to use.



Inquiry: Bunkyo Garden Gate Tower 8F