

## LINTEC Technical Information

1. Product : **R series**

2. Emboss No. : **R-133 #**

# : LINTEC (SUZHOU) TECH CORPORATION Products

3. Specification :

| Grade      | Basis Weight (g/m <sup>2</sup> ) | Thickness (μm) | Glossiness (%) |
|------------|----------------------------------|----------------|----------------|
| LXD (BC5)  | 220 ± 20                         | 360 ± 20       | 10 ± 2         |
| PXDH (BC5) | 195 ± 10                         | 330 ± 20       | 10 ± 2         |

This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty.

BC5 : Curl prevention treatment

| Grade       | Release Type  | Application      | Recommended Temperature |
|-------------|---------------|------------------|-------------------------|
| EV130TPD    | Polyolefin    | PU               | 110 – 130°C             |
| LXD         |               |                  | 110 – 130°C             |
| PXDH / PXDL |               | PU, Semi-PU, PVC | 190 – 210°C             |
| VX          | Special Resin | PVC              | 190 – 210°C             |
| ENPLUS      |               | PU, Semi-PU, PVC | 190 – 210°C             |

### -Notes

The statements in this technical information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications, customers should independently determine the suitability of this material for their specific purpose, Prior to use.



LINTEC Corporation *Linking your dreams*

Inquiry : Bunkyo Garden Gate Tower 8F

1-1-1 Koishikawa, Bunkyo-ku, Tokyo 112-0002, Japan

Phone: +81-3-3868-7721 Fax: +81-3-3868-7728

● HEAD OFFICE 23-23, Honcho, Itabashi-ku, Tokyo 173-0001, Japan

www.castingpapers.com