

LINTEC Technical Information

1. Product : **R series**

2. Emboss No. : **R-180 #**

: LINTEC (SUZHOU) TECH CORPORATION Products

3. Specification :

| Grade | Basis Weight (g/m ²) | Thickness (μm) | Glossiness (%) |
|------------|----------------------------------|----------------|----------------|
| LXD | 220 ± 20 | 350 ± 20 | 5 ± 2 |
| PXDH (BC5) | 220 ± 20 | 390 ± 20 | 5 ± 2 |

This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty.

BC5 : Curl prevention treatment

| Grade | Release Type | Application | Recommended Temperature |
|-------------|---------------|------------------|-------------------------|
| EV130TPD | Polyolefin | PU | 110 – 130°C |
| LXD | | | 110 – 130°C |
| PXDH / PXDL | | PU, Semi-PU, PVC | 190 – 210°C |
| VX | Special Resin | PVC | 190 – 210°C |
| ENPLUS | | PU, Semi-PU, PVC | 190 – 210°C |

-Notes

The statements in this technical information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications, customers should independently determine the suitability of this material for their specific purpose, Prior to use.



LINTEC Corporation *Linking your dreams*

● HEAD OFFICE 23 – 23, Honcho, Itabashi-ku, Tokyo 173-0001, Japan

Inquiry : Bunkyo Garden Gate Tower 8F

1-1-1 Koishikawa, Bunkyo-ku, Tokyo 112-0002, Japan

Phone: +81-3-3868-7721 Fax: +81-3-3868-7728

www.castingpapers.com