

LINTEC Technical Information

1. Product : **R series**

2. Emboss No. : **R-152**

3. Specification :

Grade	Basis Weight (g/m ²)	Thickness (μm)	Glossiness (%)
LXD (BC5)	200 ± 20	290 ± 30	8 ± 1.5
PXDH (BC5)	200 ± 20	290 ± 30	10 ± 2

This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty.

BC5 : Curl prevention treatment

Grade	Release Type	Application	Recommended Temperature
EV130TPD	Polyolefin	PU	110 – 130°C
LXD			110 – 130°C
PXDH / PXDL		PU, Semi-PU, PVC	190 – 210°C
VX	Special Resin	PVC	190 – 210°C
ENPLUS		PU, Semi-PU, PVC	190 – 210°C

-Notes

The statements in this technical information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications, customers should independently determine the suitability of this material for their specific purpose, Prior to use.



LINTEC Corporation *Linking your dreams*

● HEAD OFFICE 23 – 23, Honcho, Itabashi-ku, Tokyo 173-0001, Japan

Inquiry : Bunkyo Garden Gate Tower 8F

1-1-1 Koishikawa, Bunkyo-ku, Tokyo 112-0002, Japan

Phone: +81-3-3868-7721 Fax: +81-3-3868-7728

www.castingpapers.com