

## LINTEC Technical Information

1. Product : **R series**

2. Emboss No. : **R-297**

3. Specification :

Grade	Basis Weight (g/m <sup>2</sup> )	Thickness (μm)	Glossiness (%)
LXD	150 ± 10	360 ± 20	3.5 ± 1
PXDH	150 ± 10	365 ± 20	4 ± 1
VX*	—	—	—

This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty.

\* : Performance data not available

Grade	Release Type	Application	Recommended Temperature
EV130TPD	Polyolefin	PU	110 – 130°C
LXD			110 – 130°C
PXDH / PXDL		PU, Semi-PU, PVC	190 – 210°C
VX	Special Resin	PVC	190 – 210°C
ENPLUS		PU, Semi-PU, PVC	190 – 210°C

### -Notes

The statements in this technical information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications, customers should independently determine the suitability of this material for their specific purpose, Prior to use.

