

LINTEC Technical Information

1. Product : **R series**

2. Emboss No. : **R-385**

3. Specification :

| Grade | Basis Weight (g/m ²) | Thickness (μm) | Glossiness (%) |
|----------|----------------------------------|----------------|----------------|
| EV130TPD | 155 ± 10 | 280 ± 20 | 6 ± 2 |
| PXDH | 150 ± 10 | 270 ± 20 | 4 ± 1 |
| VX | 170 ± 10 | 275 ± 20 | 4 ± 1 |

This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty.

| Grade | Release Type | Application | Recommended Temperature |
|-------------|---------------|------------------|-------------------------|
| EV130TPD | Polyolefin | PU | 110 – 130°C |
| LXD | | | 110 – 130°C |
| PXDH / PXDL | | PU, Semi-PU, PVC | 190 – 210°C |
| VX | Special Resin | PVC | 190 – 210°C |
| ENPLUS | | PU, Semi-PU, PVC | 190 – 210°C |

-Notes

The statements in this technical information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications, customers should independently determine the suitability of this material for their specific purpose, Prior to use.

