

## LINTEC Technical Information

1. Product : R series

2. Emboss No. : R-61

3. Specification :

Grade	Basis Weight (g/m <sup>2</sup> )	Thickness (μm)	Glossiness (%)
EV130TPD	150 ± 7	190 ± 20	30 ± 3
PXDH	155 ± 7	200 ± 20	27 ± 4
VX	165 ± 10	195 ± 15	20 ± 4

This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty.

Grade	Release Type	Application	Recommended Temperature
EV130TPD	Polyolefin	PU	110 – 130°C
LXD			110 – 130°C
PXDH / PXDL		PU, Semi-PU, PVC	190 – 210°C
VX	Special Resin	PVC	190 – 210°C
ENPLUS		PU, Semi-PU, PVC	190 – 210°C

### -Notes

The statements in this technical information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications, customers should independently determine the suitability of this material for their specific purpose, Prior to use.

