

## LINTEC Technical Information

1. Product : **ZR series**

2. Emboss No. : **ZR-26V**

3. Specification :

Grade	Basis Weight (g/m <sup>2</sup> )	Thickness (μm)	Glossiness (%)
EV130TPD	165 ± 10	240 ± 20	9 ± 3
PXDH*	—	—	—

This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty.

\* : Performance data not available

Grade	Release Type	Application	Recommended Temperature
EV130TPD	Polyolefin	PU	110 – 130°C
LXD			110 – 130°C
PXDH / PXDL		PU, Semi-PU, PVC	190 – 210°C
VX	Special Resin	PVC	190 – 210°C
ENPLUS		PU, Semi-PU, PVC	190 – 210°C

### -Notes

The statements in this technical information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications, customers should independently determine the suitability of this material for their specific purpose, Prior to use.



**LINTEC Corporation** *Linking your dreams*

**Inquiry :** Bunkyo Garden Gate Tower 8F  
1-1-1 Koishikawa, Bunkyo-ku, Tokyo 112-0002, Japan  
Phone: +81-3-3868-7721 Fax: +81-3-3868-7728

● **HEAD OFFICE** 23 – 23, Honcho, Itabashi-ku, Tokyo 173-0001, Japan

[www.castingpapers.com](http://www.castingpapers.com)