

## LINTEC Technical Information

1. Product : **ZR series**

2. Emboss No. : **ZR-62**

3. Specification :

| Grade | Basis Weight (g/m <sup>2</sup> ) | Thickness (μm) | Glossiness (%) |
|-------|----------------------------------|----------------|----------------|
| LXD   | 170 ± 10                         | 220 ± 20       | 23 ± 5         |
| PXDH* | —                                | —              | —              |

This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty.

\* : Performance data not available

| Grade       | Release Type  | Application      | Recommended Temperature |
|-------------|---------------|------------------|-------------------------|
| EV130TPD    | Polyolefin    | PU               | 110 – 130°C             |
| LXD         |               |                  | 110 – 130°C             |
| PXDH / PXDL |               | PU, Semi-PU, PVC | 190 – 210°C             |
| VX          | Special Resin | PVC              | 190 – 210°C             |
| ENPLUS      |               | PU, Semi-PU, PVC | 190 – 210°C             |

### -Notes

The statements in this technical information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications, customers should independently determine the suitability of this material for their specific purpose, Prior to use.

